

PROHLÁŠENÍ O VLASTNOSTECH

DoP 0194

pro pro vstříkovací systém fischer FIS VL (Kovové kotvy do betonu)

CS

1. Jedinečný identifikační kód typu výrobku:

DoP 0194

2. Zamýšlené/zamýšlená použití:

Dodatečné upevnění v tažené a tlačené zóně betonu.

Viz. dodatek, obzvláště Přílohy B1- B8

3. Výrobce:

fischerwerke GmbH & Co. KG, Otto-Hahn-Straße 15, 79211 Denzlingen, Německo

4. Zplnomocněný zástupce:

-

5. Systém/systémy POSV:

1

6. Evropský dokument pro posuzování:

EAD 330499-01-0601

Evropské technické posuzení:

Subjekt pro technické posuzování:

Oznámený subjekt/oznámené subjekty:

ETA- 10/0352; 2020-05-13

DBt- Deutsches Institut für Bautechnik

1343 MPA Darmstadt / 2873 TU Darmstadt

7. Deklarovaná vlastnost/Deklarované vlastnosti:

Mechanická odolnost a stabilita (BWR 1)

Charakteristická únosnost v tahu (pro statickou a kvazistatickou akci):

Odolnost proti selhání oceli:

Přílohy C1, C2

Odolnost proti kombinovanému porušení vytažením a selháním betonu:

Přílohy C3- C5

$\tau_{Rk,100}$ = NPD

Odolnost proti selhání betonu:

Přílohy C3

Okrajová vzdálenost bránící rozštěpení při zatížení:

Přílohy C3

Pevnost:

Přílohy C3- C5

Maximální utahovací moment při instalaci:

Přílohy B3, B4

Minimální vzdálenost od okraje a rozteč:

Přílohy B3, B4

Charakteristická únosnost ve smyku (pro statickou a

kvazistatickou akci):

Odolnost proti selhání oceli:

Přílohy C1, C2

Odolnost proti selhání rozštěpením:

Přílohy C3

Odolnost proti selhání okraje betonu:

Přílohy C3

Charakteristická únosnost a posuny pro seismické kategorie C1 a C2:

Odolnost proti tahovému zatížení, posuny, kategorie C1:

NPD

Odolnost proti tahovému zatížení, posuny, kategorie C2:

NPD

Odolnost proti smykovému zatížení, posuny, kategorie C1:

NPD

Odolnost proti smykovému zatížení, posuny, kategorie C2:

NPD

Koeficient prstencové mezery:

NPD

posuny při krátkodobém a dlouhodobém zatížení:

Posuny při krátkodobém a dlouhodobém zatížení:

Přílohy C6

Hygiena, zdraví a životní prostředí (BWR 3)

Obsah, emise a / nebo uvolňování nebezpečných látek:

NPA



8. Příslušná technická dokumentace a/nebo specifická – technická dokumentace:

Vlastnosti výše uvedeného výrobku jsou ve shodě se souborem deklarovaných vlastností. Toto prohlášení o vlastnostech se v souladu s nařízením (EU) č. 305/2011 vydává na výhradní odpovědnost výrobce uvedeného výše.

Podepsáno za výrobce a jeho jménem:

Thilo Pregartner, Dr.-Ing.
Tumlingen, 2020-05-26

Peter Schillinger, Dipl.-Ing.

Toto PoV bylo připraveno v různých jazykových mutacích. V případě rozporu vždy rozhoduje interpretace verze v anglickém jazyce.

Příloha obsahuje nepovinné a doplňkové informace v anglickém jazyce nad rámec zákonného požadavků.

Specific Part

1 Technical description of the product

The "fischer injection system FIS VL" is a bonded fastener consisting of a cartridge with injection mortar fischer FIS VL, fischer FIS VL High Speed or fischer FIS VL Low Speed and a steel element according to Annex A4.

The steel element is placed into a drilled hole filled with injection mortar and is anchored via the bond between metal part, injection mortar and concrete.

The product description is given in Annex A.

2 Specification of the intended use in accordance with the applicable European Assessment Document

The performances given in Section 3 are only valid if the anchor is used in compliance with the specifications and conditions given in Annex B.

The verifications and assessment methods on which this European Technical Assessment is based lead to the assumption of a working life of the anchor of at least 50 years. The indications given on the working life cannot be interpreted as a guarantee given by the producer, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment

3.1 Mechanical resistance and stability (BWR 1)

Essential characteristic	Performance
Characteristic resistance to tension load (static and quasi-static loading)	See Annex B 3 and B 4, C 1 to C 5
Characteristic resistance to shear load (static and quasi-static loading)	See Annex C 1 to C 3
Displacements under short-term and long-term loading	See Annex C 6
Characteristic resistance and displacements for seismic performance categories C1 and C2	No performance assessed

3.2 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Content, emission and/or release of dangerous substances	No performance assessed

Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base


In accordance with the European Assessment Document EAD 330499-01-0601 the applicable European legal act is: [96/582/EC].

The system to be applied is: 1


Installation conditions part 1

fischer anchor rod


Pre-positioned installation



Push through installation (annular gap filled with mortar)



Pre-positioned or push through installation with subsequently injected fischer filling disc
(annular gap filled with mortar)



Figures not to scale

h_0 = drill hole depth

h_{ef} = effective embedment depth

t_{fix} = thickness of fixture

fischer injection system FIS VL

Product description

Installation conditions part 1


Annex A 1

Appendix 3/ 21


Installation conditions part 2

fischer internal threaded anchor RG MI

Pre-positioned installation



Pre-positioned installation with subsequently injected fischer filling disc (annular gap filled with mortar)



Figures not to scale

h_0 = drill hole depth

h_{ef} = effective embedment depth

t_{fix} = thickness of fixture

fischer injection system FIS VL

Product description



Installation conditions part 2

Annex A 2

Appendix 4/ 21

Overview system components part 1



Injection cartridge (shuttle cartridge) with sealing cap; Sizes: 350 ml, 360 ml, 390 ml, 550 ml, 1100 ml, 1500 ml



Imprint: fischer FIS VL or FIS VL High Speed or FIS VL Low Speed, processing notes, shelf-life, piston travel scale (optional), curing times and processing times (depending on temperature), hazard code, size, volume




Injection cartridge (coaxial cartridge) with sealing cap; Sizes: 100 ml, 150 ml, 300 ml, 380 ml, 400 ml, 410 ml




Imprint: fischer FIS VL or FIS VL High Speed or FIS VL Low Speed, processing notes, shelf-life, piston travel scale (optional), curing times and processing times (depending on temperature), hazard code, size, volume



Static mixer FIS MR Plus



Injection adapter and Extension tube for static mixer



Cleaning brush BS



Blow-out pump AB-G or ABP



Figures not to scale

fischer injection system FIS VL

Product description

Overview system components part 1;
cartridges / static mixer / accessories


Annex A 3

Appendix 5/ 21

Overview system components part 2

fischer anchor rod

Size: M6, M8, M10, M12, M16, M20, M24, M27, M30




fischer internal threaded anchor RG MI


Size: M8, M10, M12, M16, M20



Screw / threaded rod / washer / hexagon nut



fischer filling disc with injection adapter



Figures not to scale

fischer injection system FIS VL

Product description

Overview system components part 2;
steel components

Annex A 4

Appendix 6/ 21

Table A5.1: Materials

Part	Designation	Material		
1	Injection cartridge	Mortar, hardener, filler		
Steel grade		Steel	Stainless steel R	High corrosion resistant steel HCR
		zinc plated	acc. to EN 10088-1:2014 Corrosion resistance class CRC III acc. to EN 1993-1-4:2015	acc. to EN 10088-1:2014 Corrosion resistance class CRC V acc. to EN 1993-1-4:2015
2	Anchor rod	Property class 4.8, 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; 1.4062, 1.4662, 1.4462; EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation	Property class 50 or 80 EN ISO 3506-1:2009 or property class 70 with $f_{yk} = 560 \text{ N/mm}^2$ 1.4565; 1.4529; EN 10088-1:2014 $f_{uk} \leq 1000 \text{ N/mm}^2$ $A_5 > 8\%$ fracture elongation
3	Washer ISO 7089:2000	zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	1.4565; 1.4529; EN 10088-1:2014
4	Hexagon nut	Property class 4, 5 or 8; EN ISO 898-2:2012 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	Property class 50, 70 or 80 EN ISO 3506-1:2009 1.4565; 1.4529; EN 10088-1:2014
5	fischer internal threaded anchor RG MI	Property class 5.8 ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K)	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529; EN 10088-1:2014
6	Commercial standard screw or threaded rod for fischer internal threaded anchor RG MI	Property class 5.8 or 8.8; EN ISO 898-1:2013 zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) $A_5 > 8\%$ fracture elongation	Property class 70 EN ISO 3506-1:2009 1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014 $A_5 > 8\%$ fracture elongation	Property class 70 EN ISO 3506-1:2009 1.4565; 1.4529; EN 10088-1:2014 $A_5 > 8\%$ fracture elongation
7	fischer filling disc similar to DIN 6319-G	zinc plated $\geq 5 \mu\text{m}$, ISO 4042:2018/Zn5/An(A2K) or hot dip galvanised $\geq 40 \mu\text{m}$ EN ISO 10684:2004	1.4401; 1.4404; 1.4578; 1.4571; 1.4439; 1.4362; EN 10088-1:2014	1.4565; 1.4529; EN 10088-1:2014

fischer injection system FIS VL

Product description
Materials
Annex A 5

Appendix 7 / 21

Specifications of intended use (part 1)

Table B1.1: Overview use and performance categories

Anchorage subject to		FIS VL with ...								
		Anchor rod		fischer internal threaded anchor RG MI						
Hammer drilling with standard drill bit		all sizes								
Hammer drilling with hollow drill bit (fischer FHD, Heller "Duster Expert"; Bosch „Speed Clean“; Hilti "TE-CD, TE-YD", DreBo „D-Plus“, DreBo „D-Max“)		Nominal drill bit diameter (d_0) 12 mm to 35 mm								
Static and quasi static load, in	uncracked concrete	all sizes	Tables: C1.1 C3.1 C4.1 C6.1	all sizes	Tables: C2.1 C3.1 C5.1 C6.2					
	cracked concrete	M10 bis M20			-2)					
Use category	I1 dry or wet concrete	all sizes								
	I2 water filled hole ¹⁾	M 12 to M 30		M 8 bis M 20						
Installation direction	D3 (downward and horizontal and upwards (e.g. overhead) installation)									
Installation temperature	$T_{i,min} = -10 \text{ }^{\circ}\text{C}$ to $T_{i,max} = +40 \text{ }^{\circ}\text{C}$									
In-service temperature	Temperature range I	-40 °C to +80 °C	(max. short term temperature +80 °C; max. long term temperature +50 °C)							
	Temperature range II	-40 °C to +120 °C	(max. short term temperature +120 °C; max. long term temperature +72 °C)							
<p>¹⁾ Only with coaxial cartridges: 380ml, 400 ml, 410 ml</p> <p>²⁾ No performance assessed</p>										
fischer injection system FIS VL										
Intended use Specifications (part 1)				Annex B 1 Appendix 8/21						

Specifications of intended use (part 2)

Base materials:

- Compacted reinforced or unreinforced normal weight concrete without fibres of strength classes C20/25 to C50/60 according to EN 206:2013+A1:2016

Use conditions (Environmental conditions):

- Structures subject to dry internal conditions (zinc coated steel, stainless steel or high corrosion resistant steel).
- For all other conditions according to EN1993-1-4:2015 corresponding to corrosion resistance classes to Annex A 5 table A5.1.

Design:

- Anchorages have to be designed by a responsible engineer with experience of concrete anchor design.
- Verifiable calculation notes and drawings are to be prepared taking account of the loads to be anchored. The position of the anchor is indicated on the design drawings (e. g. position of the anchor relative to reinforcement or to supports, etc.).
- Anchorages are designed in accordance with:
EN 1992-4:2018 and EOTA Technical Report TR 055, Edition February 2018.

Installation:

- Anchor installation is to be carried out by appropriately qualified personnel and under the supervision of the person responsible for technical matters of the site
- In case of aborted hole: The hole shall be filled with mortar
- Anchorage depth should be marked and adhered to on installation
- Overhead installation is allowed

fischer injection system FIS VL

Intended use
Specifications (part 2)


Annex B 2

Appendix 9/ 21

Table B3.1: Installation parameters for anchor rods

Anchor rods		Thread	M6	M8	M10	M12	M16	M20	M24	M27	M30		
Width across flats		[mm]	10	13	17	19	24	30	36	41	46		
Nominal drill hole diameter			8	10	12	14	18	24	28	30	35		
Drill hole depth			$h_0 = h_{\text{ef}}$										
Effective embedment depth			50	60	60	70	80	90	96	108	120		
$h_{\text{ef}, \text{min}}$			72	160	200	240	320	400	480	540	600		
Minimum spacing and minimum edge distance			40	40	45	55	65	85	105	125	140		
Diameter of the clearance hole of the fixture	pre-positioned installation		7	9	12	14	18	22	26	30	33		
	push through installation		9	12	14	16	20	26	30	33	40		
Minimum thickness of concrete member			$h_{\text{ef}} + 30 (\geq 100)$				$h_{\text{ef}} + 2d_0$						
Maximum installation torque			max T_{inst}	[Nm]	5	10	20	40	60	120	150	200	300

fischer anchor rod




Marking (on random place) fischer anchor rod:

Steel zinc plated PC ¹⁾ 8.8	• or +	Steel hot-dip PC ¹⁾ 8.8	●
High corrosion resistant steel HCR PC ¹⁾ 50	•	High corrosion resistant steel HCR PC ¹⁾ 70	-
High corrosion resistant steel HCR PC ¹⁾ 80	(Stainless steel R property class 50	~
Stainless steel R property class 80	*		

Alternatively: Colour coding according to DIN 976-1:2016

¹⁾ PC = property class

Installation conditions:



Commercial standard threaded rods, washers and hexagon nuts may also be used if the following requirements are fulfilled

- Materials, dimensions and mechanical properties according to Annex A 5, Table A5.1
- Inspection certificate 3.1 according to EN 10204:2004, the documents have to be stored
- Setting depth is marked

Figures not to scale

fischer injection system FIS VL


Intended use
Installation parameters anchor rods

Annex B 3

Table B4.1: Installation parameters for **fischer internal threaded anchors RG MI**

Internal threaded anchors RG MI		Thread	M8	M10	M12	M16	M20
Diameter of anchor	$d_{\text{nom}} = d_H$	[mm]	12	16	18	22	28
Nominal drill hole diameter	d_0		14	18	20	24	32
Drill hole depth	h_0		$h_0 = h_{\text{ef}} = L_H$				
Effective embedment depth ($h_{\text{ef}} = L_H$)	h_{ef}		90	90	125	160	200
Minimum spacing and minimum edge distance	$s_{\text{min}} = c_{\text{min}}$		55	65	75	95	125
Diameter of clearance hole in the fixture	d_f		9	12	14	18	22
Minimum thickness of concrete member	h_{min}		120	125	165	205	260
Maximum screw-in depth	$l_{E,\text{max}}$		18	23	26	35	45
Minimum screw-in depth	$l_{E,\text{min}}$		8	10	12	16	20
Maximum installation torque	max T_{inst}	[Nm]	10	20	40	80	120

fischer internal threaded anchor RG MI




Marking: Anchor size e. g.: **M10**

Stainless steel → additional **R**; e.g.: **M10 R**

High corrosion resistant steel → additional **HCR**; e.g.: **M10 HCR**

Retaining bolt or threaded rods (including nut and washer) must comply with the appropriate material and strength class of Annex A 5, Table A5.1

Installation conditions:



Figures not to scale

fischer injection system FIS VL

Intended use


Installation parameters internal threaded anchors RG MI

Annex B 4

Table B5.1: Parameters of the **cleaning brush BS** (steel brush with steel bristles)

The size of the cleaning brush refers to the drill hole diameter

Nominal drill hole diameter	d_0	[mm]	8	10	12	14	16	18	20	24	25	28	30	35
Steel brush diameter BS	d_b		9	11	14	16	20		25	26	27	30		40

**Table B5.2 Maximum processing time** of the mortar and **minimum curing time**

(During the curing time of the mortar the concrete temperature may not fall below the listed minimum temperature)

Temperature at anchoring base [°C]	Maximum processing time t_{work}			Minimum curing time ¹⁾ t_{cure}		
	FIS VL High Speed	FIS VL	FIS VL Low Speed	FIS VL High Speed	FIS VL	FIS VL Low Speed
-10 to -5 ²⁾	-	-	-	12 h	-	-
> -5 to 0 ²⁾	5 min	-	-	3 h	24 h	-
> 0 to 5 ²⁾	5 min	13 min	-	3 h	3 h	6 h
> 5 to 10	3 min	9 min	20 min	50 min	90 min	3 h
> 10 to 20	1 min	5 min	10 min	30 min	60 min	2 h
> 20 to 30	-	4 min	6 min	-	45 min	60 min
> 30 to 40	-	2 min	4 min	-	35 min	30 min

¹⁾ In wet concrete or water filled holes the curing times must be doubled²⁾ Minimal cartridge temperature +5°C

fischer injection system FIS VL

Intended use







Cleaning brush (steel brush)

Processing time and curing time

Annex B 5



Installation instructions part 1

Drilling and cleaning the hole (hammer drilling with standard drill bit)

1		Drill the hole. Nominal drill hole diameter d_0 and drill hole depth h_0 see tables B3.1, B4.1		
2		Clean the drill hole: For $h_{ef} \leq 12d$ and $d_0 < 18 \text{ mm}$ blow out the hole four times by hand		For $h_{ef} > 12d$ and / or $d_0 \geq 18 \text{ mm}$ blow out the hole four times with oil-free compressed air ($p \geq 6 \text{ bar}$)
3		Brush the drill hole four times. For deep holes use an extension. Corresponding brushes see table B5.1		
4		Clean the drill hole: For $h_{ef} \leq 12d$ and $d_0 < 18 \text{ mm}$ blow out the hole four times by hand		For $h_{ef} > 12d$ and / or $d_0 \geq 18 \text{ mm}$ blow out the hole four times with oil-free compressed air ($p \geq 6 \text{ bar}$)

Go to step 5

Drilling and cleaning the hole (hammer drilling with hollow drill bit)

1		Check a suitable hollow drill (see table B1.1) for correct operation of the dust extraction
2		Use a suitable dust extraction system, e. g. fischer FVC 35 M or a comparable dust extraction system with equivalent performance data Drill the hole with hollow drill bit. The dust extraction system has to extract the drill dust nonstop during the drilling process and must be adjusted to maximum power. Nominal drill hole diameter d_0 and drill hole depth h_0 see tables B3.1, B4.1

Go to step 5

fischer injection system FIS VL

Intended use


Installation instructions part 1

Annex B 6

Appendix 13/ 21




Installation instructions part 2

Preparing the cartridge

5		Remove the sealing cap Screw on the static mixer (the spiral in the static mixer must be clearly visible)
6		Place the cartridge into the dispenser
7		Extrude approximately 10 cm of material out until the resin is evenly grey in colour. Do not use mortar that is not uniformly grey

Go to step 8

Injection of the mortar

8	 Fill approximately 2/3 of the drill hole with mortar. Always begin from the bottom of the hole and avoid bubbles	 For drill hole depth ≥ 150 mm use an extension tube	 For overhead installation, deep holes ($h_0 > 250$ mm) or drill hole diameter ($d_0 \geq 40$ mm) use an injection adapter
---	---	---	--

Go to step 9

fischer injection system FIS VL

Intended use







Installation instructions part 2

Annex B 7

Appendix 14/ 21

Installation instructions part 3

Installation of anchor rods or fischer internal threaded anchors RG MI

9	 	<p>Only use clean and oil-free metal parts. Mark the setting depth of the metal part. Push the anchor rod or fischer internal threaded RG MI anchor down to the bottom of the hole, turning it slightly while doing so. After inserting the metal parts, excess mortar must be emerged around the anchor element.</p>
	 <p>For overhead installations support the metal part with wedges (e.g. fischer centering wedges) or fischer overhead clips.</p>	 <p>For push through installation fill the annular gap with mortar</p>
10	 <p>Wait for the specified curing time t_{cure} see table B5.2</p>	 <p>11</p> <p>Mounting the fixture max T_{inst} see tables B3.1 and B4.1</p>
Option	 <p>After the minimum curing time is reached, the gap between metal part and fixture (annular clearance) may be filled with mortar via the fischer filling disc. Compressive strength $\geq 50 \text{ N/mm}^2$ (e.g. fischer injection mortars FIS HB, FIS SB, FIS V, FIS EM Plus). ATTENTION: Using fischer filling disc reduces t_{fix} (usable length of the anchor)</p>	

fischer injection system FIS VL

Intended use

Installation instructions part 3

Annex B 8

Appendix 15/ 21

Table C1.1: Characteristic values for under tension / shear load of fischer anchor rods and standard threaded rods

Anchor rod / standard threaded rod			M6	M8	M10	M12	M16	M20	M24	M27	M30										
Bearing capacity under tension load, steel failure ³⁾																					
Characteristic resistance $N_{Rk,s}$	Steel zinc plated	Property class	4.8	[kN]	8	15(13)	23(21)	33	63	98	141										
			5.8		10	19(17)	29(27)	43	79	123	177										
			8.8		16	29(27)	47(43)	68	126	196	282										
			50		10	19	29	43	79	123	177										
			70		14	26	41	59	110	172	247										
			80		16	30	47	68	126	196	282										
Partial factors ¹⁾																					
Partial factor $\gamma_{Ms,N}$	Steel zinc plated	Property class	4.8	[-]	1,50																
			5.8		1,50																
			8.8		1,50																
			50		2,86																
			70		1,50 ²⁾ / 1,87																
			80		1,60																
Bearing capacity under shear load, steel failure ³⁾																					
without lever arm																					
Characteristic resistance $V^0_{Rk,s}$	Steel zinc plated	Property class	4.8	[kN]	4	9(8)	14(13)	20	38	59	85										
			5.8		6	11(10)	17(16)	25	47	74	106										
			8.8		8	15(13)	23(21)	34	63	98	141										
			50		5	9	15	21	39	61	89										
			70		7	13	20	30	55	86	124										
			80		8	15	23	34	63	98	141										
Ductility factor			k ₇	[-]	1,0																
with lever arm																					
Charact. resistance $M^0_{Rk,s}$	Steel zinc plated	Property class	4.8	[Nm]	6	15(13)	30(27)	52	133	259	448										
			5.8		7	19(16)	37(33)	65	166	324	560										
			8.8		12	30(26)	60(53)	105	266	519	896										
			50		7	19	37	65	166	324	560										
			70		10	26	52	92	232	454	784										
			80		12	30	60	105	266	519	896										
Partial factors ¹⁾																					
Partial factor $\gamma_{Ms,V}$	Steel zinc plated	Property class	4.8	[-]	1.25																
			5.8		1.25																
			8.8		1.25																
			50		2.38																
			70		1.25 ²⁾ / 1.56																
			80		1.33																
¹⁾ In absence of other national regulations																					
²⁾ Only admissible for high corrosion resistant steel HCR, with $f_yk / f_{uk} \geq 0,8$ and $A_5 > 12\%$ (e.g. fischer anchor rods)																					
³⁾ Values in brackets are valid for undersized threaded rods with smaller stress area A_s for hot dip galvanised standard threaded rods according to EN ISO 10684:2004+AC:2009																					
fischer injection system FIS VL										Annex C 1											
Performances Characteristic values for steel failure under tension / shear load of fischer anchor rods and standard threaded rods																					
										Appendix 16/ 21											

Table C2.1: Characteristic values for steel failure under tension / shear load of fischer internal threaded anchors RG MI

fischer internal threaded anchors RG MI			M8	M10	M12	M16	M20		
Bearing capacity under tension load, steel failure									
Charact. resistance with screw	N _{Rk,s}	Property class	5.8	[kN]	19	29	43	79	123
		8.8			29	47	68	108	179
		Property class	R		26	41	59	110	172
		70	HCR		26	41	59	110	172
Partial factors¹⁾									
Partial factors	γ _{Ms,N}	Property class	5.8	[-]		1,50			
		8.8				1,50			
		Property class	R			1,87			
		70	HCR			1,87			
Bearing capacity under shear load, steel failure									
Without lever arm									
Charact. resistance with screw	V ⁰ _{Rk,s}	Property class	5.8	[kN]	9,2	14,5	21,1	39,2	62,0
		8.8			14,6	23,2	33,7	54,0	90,0
		Property class	R		12,8	20,3	29,5	54,8	86,0
		70	HCR		12,8	20,3	29,5	54,8	86,0
Ductility factor		k ₇	[-]			1,0			
With lever arm									
Charact. resistance with screw	M ⁰ _{Rk,s}	Property class	5.8	[Nm]	20	39	68	173	337
		8.8			30	60	105	266	519
		Property class	R		26	52	92	232	454
		70	HCR		26	52	92	232	454
Partial factors¹⁾									
Partial factors	γ _{Ms,V}	Property class	5.8	[-]		1,25			
		8.8				1,25			
		Property class	R			1,56			
		70	HCR			1,56			

¹⁾ In absence of other national regulations

fischer injection system FIS VL

Performances

Characteristic values for steel failure under tension / shear load of fischer internal threaded anchor RG MI

Annex C 2

Table C3.1: Characteristic values for concrete failure under tension / shear load

Size	All sizes		
Tension load			
Installation factor	γ_{inst}	[$-$]	See annex C 4 to C 5
Factors for the compressive strength of concrete > C20/25			
Increasing factor for τ_{Rk}	C25/30	Ψ_c [$-$]	1,05
	C30/37		1,10
	C35/45		1,15
	C40/50		1,19
	C45/55		1,22
	C50/60		1,26
Splitting failure			
Edge distance	$h / h_{\text{ref}} \geq 2,0$	$c_{\text{cr,sp}}$ [mm]	1,0 h_{ref}
	$2,0 > h / h_{\text{ref}} > 1,3$		4,6 h_{ref} - 1,8 h
	$h / h_{\text{ref}} \leq 1,3$		2,26 h_{ref}
Spacing	$s_{\text{cr,sp}}$		2 $c_{\text{cr,sp}}$
Concrete cone failure			
Uncracked concrete	$k_{\text{ucr,N}}$	$[-]$	11,0
Cracked concrete	$k_{\text{cr,N}}$		7,7
Edge distance	$c_{\text{cr,N}}$	$[mm]$	1,5 h_{ref}
Spacing	$s_{\text{cr,N}}$		2 $c_{\text{cr,N}}$
Factors for sustained tension load			
Temperature range	$[-]$	50 °C / 80 °C	
Factor	Ψ_{sus}^0	$[-]$	0,74
0,87			
Shear load			
Installation factor	γ_{inst}	$[-]$	1,2
Concrete pry-out failure			
Factor for pry-out failure	k_8	$[-]$	2,0
Concrete edge failure			
Effective length of fastener in shear loading	l_f	[mm]	for $d_{\text{nom}} \leq 24$ mm: min (h_{ref} ; 12 d_{nom}) for $d_{\text{nom}} > 24$ mm: min (h_{ref} ; 8 d_{nom} ; 300 mm)
Calculation diameters			
Size		M6 M8 M10 M12 M16 M20 M24 M27 M30	
fischer anchor rods and standard threaded rods	d_{nom}	6 8 10 12 16 20 24 27 30	
fischer internal threaded anchors RG MI	d_{nom}	[mm] - ¹⁾ 12 16 18 22 28 - ¹⁾ - ¹⁾ - ¹⁾	
1) Anchor type not part of the assessment			
fischer injection system FIS VL			
Performances Characteristic values for concrete failure under tension / shear load			
			Annex C 3
			Appendix 18/ 21

Table C4.1: Characteristic values for combined pull-out and concrete failure for fischer anchor rods and standard threaded rods in hammer drilled holes; uncracked or cracked concrete

Anchor rod / standard threaded rod		M6	M8	M10	M12	M16	M20	M24	M27	M30							
Combined pullout and concrete cone failure																	
Calculation diameter	d [mm]	6	8	10	12	16	20	24	27	30							
Uncracked concrete																	
Characteristic bond resistance in uncracked concrete C20/25																	
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)																	
Tem- pera- ture range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$	[N/mm ²]	9,0	11,0	11,0	11,0	10,0	9,5	9,0	8,5						
	II: 72 °C / 120 °C			6,5	9,5	9,5	9,0	8,5	8,0	7,5	7,0						
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole) ¹⁾																	
Tem- pera- ture range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$	[N/mm ²]	-2)	-2)	-2)	9,5	8,5	8,0	7,5	7,0						
	II: 72 °C / 120 °C			-2)	-2)	-2)	7,5	7,0	6,5	6,0	6,0						
Installation factors																	
Dry or wet concrete	γ_{inst}	[-]	1,2														
Water filled hole			-2)	-2)	-2)	1,4 ¹⁾											
Cracked concrete																	
Characteristic bond resistance in cracked concrete C20/25																	
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)																	
Tem- pera- ture range	I: 50 °C / 80 °C	$\tau_{Rk,cr}$	[N/mm ²]	-2)	-2)	6,0	6,0	6,0	5,5	-2)	-2)						
	II: 72 °C / 120 °C			-2)	-2)	5,0	6,0	6,0	5,0	-2)	-2)						
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole) ¹⁾																	
Tem- pera- ture range	I: 50 °C / 80 °C	$\tau_{Rk,cr}$	[N/mm ²]	-2)	-2)	-2)	5,0	5,0	4,5	-2)	-2)						
	II: 72 °C / 120 °C			-2)	-2)	-2)	4,0	4,0	4,0	-2)	-2)						
Installation factors																	
Dry or wet concrete	γ_{inst}	[-]	1,2														
Water filled hole			-2)	-2)	-2)	1,4 ¹⁾											

¹⁾ Only with coaxial cartridges: 380ml, 400 ml, 410 ml

²⁾ No Performance assessed

fischer injection system FIS VL

Performances

Characteristic values for combined pull-out and concrete failure for fischer anchor rod and standard threaded rods

Annex C 4

Appendix 19/ 21

Table C5.1: Characteristic values for combined pull-out and concrete failure for **fischer internal threaded anchors RG MI** in hammer drilled holes; **uncracked concrete**

Internal threaded anchor RG MI		M8	M10	M12	M16	M20
Combined pullout and concrete cone failure						
Calculation diameter	d [mm]	12	16	18	22	28
Uncracked concrete						
Characteristic bond resistance in uncracked concrete C20/25						
Hammer-drilling with standard drill bit or hollow drill bit (dry or wet concrete)						
Tem- perature range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$ [N/mm ²]	10,5	10,0	9,5	9,0
	II: 72 °C / 120 °C		9,0	8,0	8,0	7,5
Hammer-drilling with standard drill bit or hollow drill bit (water filled hole) ¹⁾						
Tem- perature range	I: 50 °C / 80 °C	$\tau_{Rk,ucr}$ [N/mm ²]	10,0	9,0	9,0	8,5
	II: 72 °C / 120 °C		7,5	6,5	6,5	6,0
Installation factors						
Dry or wet concrete	γ_{inst} [-]		1,2			
Water filled hole			1,4 ¹⁾			

¹⁾ Only with coaxial cartridges: 380 ml, 400 ml, 410 ml

fischer injection system FIS VL

Performances

Characteristic values for combined pull-out and concrete failure for fischer internal threaded anchors RG MI

Annex C 5

Table C6.1: Displacements for anchor rods

Anchor rod	M6	M8	M10	M12	M16	M20	M24	M27	M30
Displacement-Factors for tension load¹⁾									
Uncracked concrete; Temperature range I, II									
δ_{N0} -Factor	[mm/(N/mm ²)]	0,09	0,09	0,09	0,10	0,10	0,10	0,11	0,12
$\delta_{N\infty}$ -Factor		0,10	0,10	0,10	0,12	0,12	0,13	0,13	0,14
Cracked concrete; Temperature range I, II									
δ_{N0} -Factor	[mm/(N/mm ²)]	- ³⁾	- ³⁾	0,12	0,12	0,13	0,13	- ³⁾	- ³⁾
$\delta_{N\infty}$ -Factor		- ³⁾	- ³⁾	0,27	0,30	0,30	0,30	- ³⁾	- ³⁾
Displacement-Factors for shear load²⁾									
Uncracked or cracked concrete; Temperature range I, II									
δ_{v0} -Factor	[mm/kN]	0,11	0,11	0,11	0,10	0,10	0,09	0,09	0,08
$\delta_{v\infty}$ -Factor		0,12	0,12	0,12	0,11	0,11	0,10	0,09	0,09

¹⁾ Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed} : Design value of the applied tensile stress)

³⁾ No performance assessed

²⁾ Calculation of effective displacement:

$$\delta_{v0} = \delta_{v0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{v\infty} = \delta_{v\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed} : Design value of the applied shear force)

Table C6.2: Displacements for fischer internal threaded anchors RG MI

Internal threaded anchor RG MI	M8	M10	M12	M16	M20
Displacement-Factors for tension load¹⁾					
Uncracked concrete; Temperature range I, II					
δ_{N0} -Factor	[mm/(N/mm ²)]	0,10	0,11	0,12	0,13
$\delta_{N\infty}$ -Factor		0,13	0,14	0,15	0,16
Displacement-Factors for shear load²⁾					
Uncracked concrete; Temperature range I, II					
δ_{v0} -Factor	[mm/kN]	0,12	0,12	0,12	0,12
$\delta_{v\infty}$ -Factor		0,14	0,14	0,14	0,14

¹⁾ Calculation of effective displacement:

$$\delta_{N0} = \delta_{N0}\text{-Factor} \cdot \tau_{Ed}$$

$$\delta_{N\infty} = \delta_{N\infty}\text{-Factor} \cdot \tau_{Ed}$$

(τ_{Ed} : Design value of the applied tensile stress)

²⁾ Calculation of effective displacement:

$$\delta_{v0} = \delta_{v0}\text{-Factor} \cdot V_{Ed}$$

$$\delta_{v\infty} = \delta_{v\infty}\text{-Factor} \cdot V_{Ed}$$

(V_{Ed} : Design value of the applied shear force)

fischer injection system FIS VL

Performances

Displacements for anchor rods and fischer internal threaded anchors RG MI

Annex C 6